

TECHNICAL SPECIFICATIONS

PRE - MET PRODUCT	
Tensile properties 500 mm/min 15 mm width strip	12 µm PRE - MET
<i>Machine direction</i>	
thickness avg. (µm)	12
1% Secant modulus (MPa)	225
10% offset yield stress (MPa)	30
Tensile at break (MPa)	160
Elongation at break (%)	165
Energy to break (mJ/mm ³)	74
<i>Transverse direction</i>	
thickness avg. (µm)	12
1% Secant modulus (MPa)	360
10% offset yield stress (MPa)	8
Tensile at break (MPa)	29
Elongation at break (%)	700
Energy to break (mJ/mm ³)	78
Elmendorf Tear (g/µm)	
MD	12
TD	38
Dart drop (g)	
60	
Puncture resistance	
Maximum force (N/µm)	6,8
Travel at F max (mm)	75
Energy at Fmax (mJ/µm)	150

All these figures are typical values with tolerances 10% .

E.P.M. Stretch Films are ecologically non pollutant, absolutely non-toxic , chlorine free and can be 100% recycled

Rev: 20 - Data: novembre 2020