

# TECHNICAL SPECIFICATIONS

PRE - MET PRODUCT	
<b>Tensile properties 500 mm/min</b> 15 mm width strip	<b>9 µm PRE - MET</b>
<i>Machine direction</i>	
<b>thickness avg. (µm)</b>	<b>9</b>
1% Secant modulus (MPa)	221
10% offset yield stress (MPa)	28,5
Tensile at break (MPa)	145
Elongation at break (%)	130
Energy to break (mJ/mm <sup>3</sup> )	69
<i>Transverse direction</i>	
<b>thickness avg. (µm)</b>	<b>9</b>
1% Secant modulus (MPa)	352
10% offset yield stress (MPa)	7,2
Tensile at break (MPa)	26
Elongation at break (%)	620
Energy to break (mJ/mm <sup>3</sup> )	72
<b>Elmendorf Tear (g/µm)</b>	
MD	10
TD	35
<b>Dart drop (g)</b>	
	<b>45</b>
<b>Puncture resistance</b>	
Maximum force (N/µm)	6
Travel at F max (mm)	49
Energy at Fmax (mJ/µm)	100

All these figures are typical values with tolerances 10% .

E.P.M. Stretch Films are ecologically non pollutant, absolutely non-toxic , chlorine free and can be 100% recycled

Rev: 20 - Data: novembre 2020